



GR 241

Technical Data

SPECIFICATIONS:

Particle Size Distribution (μm)	50 - 230
Absorption Capacity (g/g 0.9% Saline)	> 60
Bulk Density (g/l)	400 - 800
Moisture (%)	< 7

Chemistry:	Sodium Acrylate polymer
Appearance:	Free flowing white granules
Storage:	Indefinite providing unopened containers/bags stored in dry conditions
Packaging:	Multi-wall bags and supersacks

Technical information is based on current knowledge and is offered to inform and advise subject to your further investigation and verification. Modifications may be made in the interest of technical improvement. No warranties are expressed or implied as the use of the product is beyond our control.

Stewart Superabsorbents LLC
1954 Main Avenue SE
Hickory, NC 28602 USA
T: +1 828 855 9316 F: +1 828 855 9319
www.stewartsuperabsorbents.com
A member of The Stewart Group of companies

Richard Ellis
Cable Materials Inc.
T: +1 678 691 6398
M: +1 678 848 4805
E: rellisga@cablematerialsinc.com