



WKR 8

Technical Data

APPLICATION: Coating of Substrates such as yarns and nonwovens

Single-component system typically cured at 170°C to produce a water-swellable coating/film.

SPECIFICATIONS:

Viscosity (RC2@10rpm)	<3000 - 5000 cps
Absorption Capacity (g/g deionized water)	> 30
pH	5.0 – 6.0
Active Content (%)	30 – 34 %

Chemistry: Water-based acrylic polymer
Appearance: Liquid
Storage: One year in unopened containers above 0°C
Packaging: Drums and Totes

Technical information is based on current knowledge and is offered to inform and advise subject to your further investigation and verification. Modifications may be made in the interest of technical improvement. No warranties are expressed or implied as the use of the product is beyond our control.

Stewart Superabsorbents LLC
1954 Main Avenue SE
Hickory, NC 28602 USA
T: +1 828 855 9316 F: +1 828 855 9319
www.stewartsuperabsorbents.com
A member of The Stewart Group of companies

Richard Ellis
Cable Materials Inc.
T: +1 678 691 6398
M: +1 678 848 4805
E: rellisga@cablematerialsinc.com